ROC'S PST/PTO 1 8 APR 2005 (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization International Bureau



10/531706

(43) International Publication Date 17 June 2004 (17.06.2004)

PCT

(10) International Publication Number WO 2004/050377 A1

(51) International Patent Classification⁷: C09D 17/00, C09C 1/30

B41M 5/00,

(21) International Application Number:

PCT/EP2003/012877

(22) International Filing Date:

18 November 2003 (18.11.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

102 56 267.9

3 December 2002 (03.12.2002)

(71) Applicant (for all designated States except US): DE-GUSSA AG [DE/DE]; Bennigsenplatz 1, 40474 Düsseldorf (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): BATZ-SOHN, Christoph [DE/DE]; Riedstrasse 10a, 63454 Hanau (DE). SCHARFE, Thomas [DE/DE]; Wartbergstrasse 20/1, 74076 Heilbronn (DE). LORTZ, Wolfgang [DE/DE]; Feldstrasse 9, 63607 Wächtersbach (DE).


- (74) Common Representative: DEGUSSA AG; Intellectual Property Management, Patente und Marken, Standort Hanau, Postfach 13 45, 63403 Hanau (DE).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).

Declarations under Rule 4.17:

as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP,

[Continued on next page]

(54) Title: DISPERSION, COATING SLIP AND ABSORPTIVE MEDIUM



(57) Abstract: Stable, aqueous dispersion containing powders A and B, - wherein powder A is an amorphous silicon dioxide powder having an average particle diameter of 0.05 to 0.7 µm and a BET surface area of 5 to 50 m²/g, and - wherein powder B is a metal oxide or non-metal oxide powder consisting of aggregates of intergrown primary particles and displays a primary particle size of 5 to 50 nm and a BET surface area of 50 to 400 m²/g. Coating slip to form an ink-absorptive coating using the dispersion and at least one hydrophilic binder. Absorptive medium using the coating slip and a support.